

# GATOR BLOCK BOND XP LOW VOC POLYURETHANE ADHESIVE

TDS Revision Date (dd/mm/yyyy): 21/03/2025



### **TECHNICAL DATA SHEET**

**Update:** March 21, 2025

Make sure you have an updated data sheet on hand. Canada and U.S. dial **1-855-847-7767** or (450) 624-1611

Description: GATOR BLOCK BOND ADHESIVE is one of the strongest polyurethane adhesives on the market. It is

especially formulated for bonding concrete, natural stones, blocks, bricks and pavers. **GATOR BLOCK BOND ADHESIVE** is intended to provide a permanent bond to approved materials such as artificial turf. **GATOR BLOCK BOND ADHESIVE** can be used on dry or humid surfaces. Drying times vary depending on

factors such as humidity, porosity, temperature and materials bonded together.

**Ideal for:** • Overlays & pool copings

Steps & wall caps

• Fire pits (up to 400°F (204°C))

Concrete pavers & bricks

Dry & damp surfaces

Permanent bond in 24 hrs

Retaining Walls

Stones

Outdoor porcelain tiles

· Artificial turf

Features:

- Permanent Bond in 24 hours
- Long open time repositioning up to 30 minutes
- Works above 32°F / 0°C
- High solids provides excellent coverage
- Non-shrinking does not crack or lose bond
- Xtra Bond Strength (up to 3 times the strength of conventional adhesives)
- Xtra Durability against torsion and tension
- Waterproof
- VOC compliant
- · Low odor

### PLEASE NOTE:

- Wear gloves during application of adhesive; once cured, material cannot be removed.
- · Not intended for applications with continuous submersion.
- If adhesion to a substrate is questionable, a test application must be conducted.
- To ensure optimal adhesion, make sure that the concrete or stone surfaces are clean and free of any foreign matter.
- Material may be repositioned for up to 30 minutes without losing bond strength. Moisture will shorten the open time of polyurethane adhesives. Avoid use when raining or onto standing water.
- **GATOR BLOCK BOND XP LOW VOC** polyurethane adhesive forms a tenacious bond overnight. Cure time varies with temperature, humidity, and the porosity of the materials joined.
- Clean all tools and equipment immediately after use with mineral solvent or an equivalence. Cured material must be mechanically removed.
- Proper application is the responsibility of the user.



www. alliance gator. com-Email: info@alliance gator. com



# GATOR BLOCK BOND XP LOW VOC POLYURETHANE ADHESIVE

TDS Revision Date (dd/mm/yyyy): 21/03/2025



#### Application instructions:

- A. Always refer to the latest GATOR BLOCK BOND XP LOW VOC <u>Technical Data Sheet (TDS)</u> at <u>AllianceGator.com</u> before installing GATOR BLOCK BOND XP LOW VOC.
  - B. Make sure that the surfaces you are bonding together are clean.
- 2. Cut the spout and puncture a hole in the cartridge with a nail.
- 3. Using a caulking gun, apply **GATOR BLOCK BOND ADHESIVE** on the clean surfaces. If **GATOR BLOCK BOND ADHESIVE** is used with **GATOR XTURF**, apply in a serpentine pattern over **GATOR XTURF Seam Tape for XTRA** performance and permanent adhesion.
- 4. Join the two surfaces firmly, use twisting motion. **GATOR BLOCK BOND ADHESIVE** works at above-freezing temperatures. Material may be repositioned up to 30 minutes without losing bond strength. Moisture will shorten the open time of polyurethane adhesives. Avoid use when raining or onto standing water. Coverage: Provides approximately 30 linear feet of 1/4" bead.

Composition: GATOR BLOCK BOND XP LOW VOC POLYURETHANE ADHESIVE is a high-content polyurethane elastomer

that cures by reaction with atmospheric moisture.

Curing time: GATOR BLOCK BOND XP LOW VOC POLYURETHANE ADHESIVE forms a tenacious bond overnight.

Cure time varies with temperature, humidity, and the porosity of the materials joined.

Adhesive24hr7 daysstrength chart:Concrete to concrete850 psi1000 psi

Coverage:

GATOR XP POLYURETHANE ADHESIVE - XTRA PERFORMANCE COVERAGE FOR 1/4" BEAD (APPROX.)			
10 oz. / 296 ml		28 oz / 828 ml	
ft	m	ft	m
28-32	8.5-9.5	79-90	24-27

Clean up: Clean all tools and equipment immediately after use with mineral solvent or an equivalence. Cured material must be mechanically removed.

Packaging: Product Size Cartridges Boxes
per Box per Pallet
GATOR BLOCK BOND XP LOW VOC POLYURETHANE ADHESIVE 10 oz / 296 ml 12 90
GATOR BLOCK BOND XP LOW VOC POLYURETHANE ADHESIVE 28 oz / 828 ml 12 60

**Storage:** Boxes / Pallets have to be stored inside. Store in a cool, dry area away from direct sunlight. The inside

storage unit has to be heated during the winter. Storing at elevated temperatures will reduce shelf life.

**Shelf life:** 1 year when properly stored.

 Working or open time
 Up to 1 hr

 Flash point
 250°F (121°C)

 Shrinkage
 None

**Specifications:** Exceeds ASTM D3498 and ASTM C557



www. alliance gator. com-Email: info@alliance gator. com